

**IN THE CLAIMS:**

Please amend the claims as follows:

---

1. (Previously Amended) A semiconductor device comprising:  
a wiring formed over a substrate, the wiring comprising a tungsten nitride film and a tungsten film formed thereon,

C1 wherein the wiring include at least one inert element, and 90% or more of the inert element is argon, and

wherein an amount of sodium contained within the wiring is equal to or less than 0.3 ppm.

2. (Currently Amended) A The device according to claim 1, wherein a thickness of the tungsten nitride film is 10 to 50 nm and a thickness of the tungsten film is 200 to 400 nm.

3. (Currently Amended) A The device according to claim 1, wherein electrical resistivity of the wiring is equal to or less than  $40 \mu\Omega\text{cm}$ .

4. (Currently Amended) A semiconductor device comprising:  
a wiring formed over a substrate, the wirings comprising a metal film and a nitride film of the metal film,

wherein the metal film is located on the nitride film of the metal film,

wherein the wiring includes at least one inert element and 90% or more of the inert element is argon, and

wherein an amount of sodium contained within the wiring is equal to or less than 0.3 ppm.

5. (Currently Amended) A The device according to claim 4, further comprising a semiconductor film adjacent to the wiring with an insulating film interposed therebetween.

6. (Currently Amended) A The device according to claim 4, wherein the inert element except for argon is contained within the wiring at an amount equal to or less than 1 atom%.

C1  
Cont.  
7. (Currently Amended) A The device according to claim 4, wherein the inert element except for argon is contained within the wiring at an amount equal to or less than 0.1 atom%.

8. (Currently Amended) A The device according to claim 4, wherein the inert element except for the argon is Xe or Kr.

9. (Currently Amended) A The device according to claim 4, wherein internal stress of the wiring is from  $-1 \times 10^{10}$  dyn/cm<sup>2</sup> to  $+1 \times 10^{10}$  dyn/cm<sup>2</sup>.

10. (Currently Amended) A The device according to claim 4, wherein line width of the wiring is equal to or less than 5μm.

11. (Currently Amended) A The device according to claim 4, wherein film thickness of the wiring is equal to or greater than 0.1 μm, and equal to or less than 0.7μm.

12. (Currently Amended) A The device according to claim 4, wherein the wiring is used as a gate electrode of a TFT.

13. (Currently Amended) A The device according to claim 4, wherein resistance value per 1 square  $\mu\text{m}$  of surface area of a connection between the wiring and an aluminum wiring is equal to or less than  $40\Omega$ .

14. (Currently Amended) A The device according to claim 4, wherein the semiconductor device is selected from the group consisting of an active matrix type liquid crystal display, an active matrix type EL display, and an active matrix type EC display.

15. (Currently Amended) A The device according to claim 4, wherein the semiconductor device is at least one electric device selected from the group consisting of a video camera, a digital camera, a projector, a goggle type display, a car navigation system, a personal computer, and a portable information terminal.

16. (Previously Amended) A semiconductor device comprising:  
a wiring formed over a substrate, the wiring comprising a tungsten nitride film and a tungsten film formed thereon; and  
an insulating film formed over the wiring, said insulating film comprising  $\text{SiOxNy}$ ,  
wherein the wiring includes at least one inert element and 90% or more of the inert element is argon, and

wherein an amount of sodium contained within the wiring is equal to or less than 0.3 ppm.

17. (Currently Amended) A The device according to claim 16, further comprising a semiconductor film adjacent to the wiring with an insulating film interposed therebetween.

18. (Currently Amended) A The device according to claim 16, wherein the inert element except for argon is contained within the wiring at an amount equal to or less than 1 atom%.

19. (Currently Amended) A The device according to claim 16, wherein the inert element except for argon is contained within the wiring at an amount equal to or less than 0.1 atom%.

20. (Currently Amended) A The device according to claim 16, wherein the inert element except for argon is Xe or Kr.

21. (Currently Amended) A The device according to claim 16, wherein internal stress of ~~the tungsten film or of~~ the wiring is from  $-1 \times 10^{10}$  dyn/cm<sup>2</sup> to  $+1 \times 10^{10}$  dyn/cm<sup>2</sup>.

22. (Currently Amended) A The device according to claim 16, wherein line width of the wiring is equal to or less than 5μm.

23. (Currently Amended) A The device according to claim 16, wherein film thickness of the wiring is equal to or greater than 0.1μm, and equal to or less than 0.7μm.

24. (Currently Amended) A The device according to claim 16, wherein the wiring is used as a gate electrode of a TFT.

25. (Currently Amended) A The device according to claim 16, wherein resistance value per 1 square μm of surface area of a connection between the wiring and an aluminum wiring is equal to or

less than  $40\Omega$ .

26. (Currently Amended) A The device according to claim 16, wherein the semiconductor device is selected from the group consisting of an active matrix type liquid crystal display, an active matrix type EL display, and an active matrix type EC display.

C1  
cont.  
27. (Currently Amended) A The device according to claim 16, wherein the semiconductor device is at least one electric device selected from the group consisting of a video camera, a digital camera, a projector, a goggle type display, a car navigation system, a personal computer, and a portable information terminal.

28. (Previously Amended) A semiconductor device comprising:  
a wiring formed over a substrate having a lamination structure comprising a phosphorus doped silicon, a nitride film of tungsten, and a film comprising tungsten,  
wherein the film comprising tungsten includes at least one inert element, and 90% or more of the inert element is argon, and  
wherein an amount of sodium contained within the wiring is equal to or less than 0.3 ppm.

29. (Currently Amended) A The device according to claim 28, wherein the wiring is further comprising a semiconductor film adjacent to the wiring with an insulating film interposed therebetween.

30. (Currently Amended) A The device according to claim 28, wherein the inert element

except for argon is contained within the wiring at an amount equal to or less than 1 atom%.

31. (Currently Amended) A The device according to claim 28, wherein the inert element except for argon is contained within the wiring at an amount equal to or less than 0.1 atom%.

32. (Currently Amended) A The device according to claim 28, wherein the inert element except for argon is Xe or Kr.

33. (Currently Amended) A The device according to claim 28, wherein internal stress of the ~~tungsten film or of the film having the tungsten compound as its main constituent~~ wiring is from  $-1 \times 10^{10}$  dyn/cm<sup>2</sup> to  $+1 \times 10^{10}$  dyn/cm<sup>2</sup>.

34. (Currently Amended) A The device according to claim 28, wherein line width of the wiring is equal to or less than 5μm.

35. (Currently Amended) A The device according to claim 28, wherein film thickness of the wiring is equal to or greater than 0.1μm, and equal to or less than 0.7μm.

36. (Currently Amended) A The device according to claim 28, wherein the wiring is used as a gate electrode of a TFT.

37. (Currently Amended) A The device according to claim 28, wherein resistance value per 1 square μm of surface area of a connection between the wiring and an aluminum wiring is equal to or

less than 40  $\Omega$ .

38. (Currently Amended) A The device according to claim 28, wherein the semiconductor device is selected from the group consisting of an active matrix type liquid crystal display, an active matrix type EL display, and an active matrix type EC display.

C1  
Cont.  
39. (Currently Amended) A The device according to claim 28, wherein the semiconductor device is an at least one electric device selected from the group consisting of a video camera, a digital camera, a projector, a goggle type display, a car navigation system, a personal computer, and a portable information terminal.

40. (Previously Amended) A semiconductor device comprising:  
a wiring formed over a substrate, the wiring having a lamination structure containing a tungsten nitride film and a film comprising tungsten formed thereon,  
wherein the film comprising tungsten includes at least one inert element, and 90% or more of the inert element is argon,  
wherein an amount of sodium contained within the wiring is equal to or less than 0.3 ppm,  
and  
wherein an amount of oxygen contained within the wiring is equal to or less than 1 wt%.

41. (Currently Amended) A The device according to claim 40, further comprising a semiconductor film adjacent to the wiring with an insulating film interposed therebetween.

42. (Currently Amended) A The device according to claim 40, wherein the inert element except for argon is contained within the wiring at an amount equal to or less than 1 atom%.

43. (Currently Amended) A The device according to claim 40, wherein the inert element except for argon is contained within the wiring at an amount equal to or less than 0.1 atom%.

CI  
cont.  
44. (Currently Amended) A The device according to claim 40, wherein the inert element except for argon is Xe or Kr.

45. (Currently Amended) A The device according to claim 40, wherein internal stress of the tungsten film or of the film having the tungsten compound as its main constituent wiring is from  $-1 \times 10^{10}$  dyn/cm<sup>2</sup> to  $+1 \times 10^{10}$  dyn/cm<sup>2</sup>.

46. (Currently Amended) A The device according to claim 40, wherein line width of the wiring is equal to or less than 5μm.

47. (Currently Amended) A The device according to claim 40, wherein film thickness of the wiring is equal to or greater than 0.1 μm, and equal to or less than 0.7 μm.

48. (Currently Amended) A The device according to claim 40, wherein the wiring is used as a gate electrode of a TFT.

49. (Currently Amended) A The device according to claim 40, wherein resistance value per 1



square  $\mu\text{m}$  of surface area of a connection between the wiring and an aluminum wiring is equal to or less than  $40\ \Omega$ .

50. (Currently Amended) A The device according to claim 40, wherein the semiconductor device is selected from the group consisting of an active matrix type liquid crystal display, an active matrix type EL display, and an active matrix type EC display.

C1  
Cont.  
51. (Currently Amended) A The device according to claim 40, wherein the semiconductor device is at least one electric device selected from the group consisting of a video camera, a digital camera, a projector, a goggle type display, a car navigation system, a personal computer, and a portable information terminal.

52. (Currently Amended) A semiconductor device comprising:  
a wiring formed over a substrate, the wiring comprising a tungsten nitride film and a film comprising tungsten formed thereon,  
wherein the wiring includes at least one inert element, and 90% or more of the inert element is argon,  
wherein an amount of sodium contained within the wiring is equal to or less than 0.3 ppm,  
and  
wherein internal stress of the wiring ~~comprising tungsten~~ is from  $-1 \times 10^{10}\ \text{dyn/cm}^2$  to  $+1 \times 10^{10}\ \text{dyn/cm}^2$ .

53 (Withdrawn).

54 (Withdrawn).

55 (Withdrawn).

56 (Withdrawn).

57 (Withdrawn).

58 (Withdrawn).

59 (Withdrawn).

60 (Withdrawn).

61 (Withdrawn).

62 (Withdrawn).

63 (Withdrawn).

C1